

M0801-30 MICCA MASON® CONCRETE ACRYLIC SEALER-CLEAR FINISH-LOW VOC

DESCRIPTION

M0801-30 is a solvent base, clear acrylic sealer that has excellent exterior durability. It is fast drying with excellent hardness, good chemical and abrasion resistance. A high gloss finish that enhances and preserved the natural beauty of uni-stone or concrete for long periods of time.

RELATED PRODUCTS: M0801-15, M0801-20, M0801-30; M0801-40;

USAGE:

Recommended for exterior use on all porous surfaces such as; concrete stone, brick and cement to protect against damaging effects of water, sunlight (UV), chemicals, petroleum spills and de-icing salt.

SURFACE PREPARATION:

The surfaces to be painted must be clean, dry, void of old flaking paint and free from all other contaminants. Any efflorescence must be cleaned with dilute muriatic acid, then rinsed well with tap water and dry. It is recommended that new cement be aged for one month before coating.

DIRECTIONS FOR USE:

Stir well before using. Apply at a temperature between 10-30° Celsius, using brush, roller or spray equipment. For a Wet Look apply two coats. Do not apply too thick in single coat as it may cause premature failure. Do not apply when rain is imminent within 36 hours. Clean equipment with Micca Thinner M0063-00.

VENTILATE WELL WORK AREA.

STORAGE: Keep the product in a dry and cool area. Keep away from open flames and sparks. The storage temperature is : (5- 30) °C.

THINNING/CLEANUP:

Do not thin. Because this product is quick drying, keep container closed when not in use. Clean brushes and equipment with M0063-00.

SAFETY INFORMATION: Lead: None. Flash point(T.C.C): -20°C.

DANGER. Highly Flammable liquid and vapour. Causes skin irritation.May be fatal if swallowed and enter airways. May cause drowsiness or dizziness. Wear protective eyewear, waterproof gloves, and protective clothing.Do not breathe vapor. Wear respiratory protection.Obtain special instructions before use.Do not handle until all safety precautions have been read and understood. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.

Store locked up.Keep out of reach children.IF IN EYES: Rinse cautiously with water for several minutes and remove contacts if present and easy todo.Continue rinsing and get medical attention if eye irritation persists.IF INHALED: Remove person to fresh air and keep comfortable for breathing.IF ON SKIN(or hair): Remove /Take off immediately all contaminated clothing.Rinse skin with water /shower.IF SWALLOWED: Rinse mouth.**DO NOT INDUCE VOMITING.**Immediately call a **POISON CENTER/Doctor. IF exposed or concerned: Get medical advice/attention.**

Consult the form of safety data (SDS) and an other information on label before using this product.

Color: Clear Liquid.

Gloss: NA

PH : NA

Viscosity : 70 ± 2 KU **Den-**
sity: 0.88 ± 0.03

Odor: Aromatic odour

Volatile Organic Compounds (VOC) 398 Grams/Liter

Flash point(T.C.C): -20°C.

Composition:

Resin type: Acrylic.

Solvent: Aromatic and Acetone.

Weight per Gallon:

7.33 ± 0.25% lb/gal.

Solids by weight: 30 ± 1%

Solids by volume: 23 ± 1%

Film Thickness:

Wet (WFT) : 4.3-7.0 mils

Dry (DFT): 1.0-1.5 mils,
(25.0-37.5 microns).

Theoretical coverage:

369 sq ft/gal, 9.0 m2/L,
@1-mils DFT

Practical coverage:

(At an effeciency of 85%)

The coverage is 314 sq ft / gal,
7.7m2 / L @ 1 mils DFT dry film thickness)

Dry Time @ 77° F (25° C) @
50% RH

Dry to touch: 15 Min

Hard to dry: 12 hours @ 25 °C

Clean Up : M0063-00.

Packaging:

Available sizes:

18,9 L & 3,79 L.



WASTE DISPOSAL:

Reach your municipality about proper disposal procedure or give leftover paint to someone who could use it, a neighbor or friend, a recreational service or a non-profit organization. For more information, visit www.eco-peinture.ca if you reside in Quebec. Do not leftover paint down the drain.

PHYSICAL PROPERTIES:

The values shown are theoretical and may vary slightly from the finished product.

WARRANTY:

In lieu of all other warranties or guarantees, express or implied, by contract or law, manufacturer's liability hereby limited to replacement of the merchandise herein if found to be defective upon inspection by it. Manufacturer shall no be liable for any representations, warranties (express or implied) made by any of its agents, representatives or employees regarding the merchandise or product contained herein.

Revision Date: 19/01/2016.

Application

Temperature (°C): 10 to 30 °C
(50° to 86 °F)

Humidity: Ideal: 50%. Max: 65%.

Equipment Recommendation
(Comparable Equipment Also Suitable).

Brush: Use a natural bristles
Brush.

Roller : Use a sheepskin roller

AIRLESS SPRAY :

Fluid Pressure: 1,500 – 2500PSI;
Tip size: .013 - .015 .in

