

**M0891-00 MICCA MASON® ANTI-SKID PAINT (SOLVENT BASED)****DESCRIPTION**

A high viscosity, heavy duty coating based on a highly polymeric organic resin formulated to give long lasting exterior durability. Protects and beautifies above grade exterior surfaces.

**RELATED PRODUCTS:**

**M0891-00 WHITE — M0891-20 MEDIUM BASE —M0891-60 ACCENT BASE.**

**USAGE:**

Recommended for above grade exterior surfaces such as concrete walls, columns, spandrels, median divider, retaining walls, concrete blocks and cement. Used also as anti-skid coating for concrete floors.

**DIRECTION FOR USE:**

Stir thoroughly before and during use. Paint is supplied in a ready to use consistency, if necessary thin up to 5 % by volume of M0061-00 Micca Thinner. Apply at a temperature between 10 -30°C using brush, roller or spray equipment. Depending on surface conditions, a second coat maybe necessary for best results. Do not apply in direct sunlight. Avoid painting to extend in early evening hours as cool conditions may facilitate condensation on the surface of the paint. Do not apply if rain is imminent in the next 24-48 hours or over frozen surface. Clean equipment with Micca Thinner M0061-00.

**SURFACE PREPARATION:**

Surfaces to be painted must be clean, dry and free from all surface contaminants. For new concrete, wash surface thoroughly with dilute muriatic acid (10 %) until acid ceases to effervesce. Repair areas where necessary then etch as per new concrete. When using muriatic acid, use rubber apron, chemical goggles with side shield, rubber gloves and protective clothing. For old painted surfaces of unknown origin, test a small areas and check for reaction with the new paint. If old paint is being dissolved or any signs of incompatibility, sandblast the whole surface. Glossy surface should be dulled. Wash thoroughly with tsp solution followed with a thorough rinse of tap water. Allow surface to dry completely before applying paint.

Caution: Removal of old paint by sanding, scraping or other means may generate dust or fumes which may contain lead. Exposure to lead dust or fumes may cause adverse health effects. Use NIOSH approved mask for dust, fumes and vapour to minimize exposure to lead.

**Caution:** Sanding, scraping and other means to remove the old paint may generate dust or fumes that contain lead. This dust and vapors can cause unwanted sidee health effects. Use a face mask against dusts and vapors NIOSH approved to minimize exposure to those latter which contain lead.

**COVERAGE:**

Based on the theoretical value without loss. Coverage may vary according to application method, texture and porosity of the surface.

**LIMITATIONS:**

Avoid painting in direct sunlight on a hot surface or if the relative humidity exceeds 85%.

**STORAGE:** Keep away from open flames and sparks. The storage temperature is (5- 30) ° C.

**Appearance:** White Liquid.

**Odor:** Mild

**Gloss Level:** Low Gloss.

**Viscosity:** 100 ± 3 KU

**Density:** 1.27 ± 0.01

**PH à 100% :** N/A

**Composition:**

**Resin Type:** polymeric resin solvent based.

**Pigment Type:** Titanium Dioxide

**Solvents/Thiner:** Mineral Spirits and xylene.

**Weight per Gallon:**

10.64 ± 0.25% lb/gal.

**Solids by weight :** 54 ± 2%

**Solids by volume :** 29 ± 2%

**Film Thickness:**

Wet : 3.4– 5.2 mil

Dry 1.0 – 1.5 mil

**Theoretical Coverage:**

11.41 m2 /litre

465.17 ft2 /gal at 1 mil DFT.

**Practical Coverage:**

9.70 m2 /litre

(396 ft2/ gal) 1.0 mil DFT.

**Dry Times:**

@ 68-77 ° F (20-25 "C), relative humidity 50% Rh

**Tack Free:** 8-16 hours

**Recoat:** 24-48 hours

**Shelf life:** 05 years, in unopened containers properly stored in a cool dry area.

**Packaging Size:**

1 Gallon=3.78L- Pails 18.9 L.

**M0891-00 MICCA MASON® ANTI-SKID PAINT (SOLVENT BASED)**

**SAFETY INFORMATION:**

Flashpoint(T.C.C): 24° C — Lead: None.

**DANGER:**

Flammable liquid and vapour. May be fatal if swallowed and enter airways. Causes mild skin irritation. Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. **Store locked up. Keep out of reach children.** No smoking. Wear protective eyewear, waterproof gloves, and protective clothing. Keep cool. Protect from sunlight.

If in eyes: Rinse cautiously with water for several minutes and

remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists.

If on skin: Wash with plenty of soap and water.

If Inhaled: Remove person to fresh air and keep comfortable for breathing

**If swallowed:** Rinse mouth. **DO NOT INDUCE VOMITING.** Immediately call a **POISON CENTER/Doctor.**

Consult the form of safety data (SDS) and an other information on label before using this product.

**WASTE DISPOSAL:**

Reach your municipality about proper disposal procedure or give leftover paint to someone who could use it, a neighbor or friend, a recreational service or a non-profit organization. For more information, visit [www.eco-peinture.ca](http://www.eco-peinture.ca) if you reside in Quebec. Do not leftover paint down the drain.

**PHYSICAL PROPERTIES:**

The values shown are theoretical and may vary slightly from the finished product.

**WARRANTY:**

In lieu of all other warranties or guarantees, express or implied, by contract or law, manufacturer's liability hereby limited to replacement of the merchandise herein if found to be defective upon inspection by it.

Manufacturer shall not be liable for any representations, warranties (express or implied) made by any of its agents, representatives or employees regarding the merchandise or product contained herein.

Issue Date : 04/11/2016.

**Application**

**Humidity:** Ideal: 50%. Maximum: 85%.

**Recommended temperatures during application:**

Material: 50 to 86°F / 10 at 30 °C

Ambient: 50a 86° F / 10 at 30 ° C

Substrate: 50a 86 °F /10 at 30 ° C

**Equipment Recommendation**

(Comparable Equipment Also Suitable).

**Brush:** Nylon / polyester high quality

**Roller:** Use a synthetic bristle muff 15 to 20mm.

**Spray:** Airless.

Pressure: 1800-2500 psi.

Spray tip 0.013- 0.015.

