

**DESCRIPTION**

A high gloss hammertone finish, based on a fast dry alkyd with very good corrosion resistance and durable finish. Depth definition of hammertone is excellent. .

**RELATED PRODUCTS:**

M2058-00 HAMMER TONE GREY RANGE OF COLORS

**USAGE:**

Recommended for maintenance of steel structures and equipment. For galvanized steel and aluminum a tie coat of M0271-00 should be used first before applying primer.

For best results, apply (2) two coats of finish.

**SURFACE PREPARATION:**

**New steel:** Remove all foreign matter such as oil, grease, soil drawing and cutting compounds and other surface contaminants by the use of appropriate solvent. If present, remove loose mill scale and loose rust by hand brushing, sanding or other hand impact or power tools. Apply primer as recommended.

**Old steel :** (painted and unpainted surface)

Remove all loose mill scale, loose rust and loose paint with power brushes, power grinders or power sanders. Check compatibility of primer on old painted surface by making a small test patch before priming the whole surface

**DIRECTIONS FOR USE:**

Stir well before using. Material is supplied in a ready to use consistency. Apply at a temperature between 10-30 °C using spray equipment. Clean tools with Micca thinner M0060-00 or M0061-00. Check compatibility with primer by making a small test patch

**STORAGE:** Keep the product in a dry and cool area. Keep away from open flames and sparks. The storage temperature is : (5- 30) °C.

**SAFETY INFORMATION:** Lead: None

**DANGER.** Flammable liquid and vapour. Causes mild skin irritation. May be fatal if swallowed and enter airways. May cause cancer. May cause genetic defects. May cause respiratory irritation. May cause drowsiness or dizziness.

Wear protective eyewear, waterproof gloves, and protective clothing.

Store locked up. Keep cool. Protect from sunlight. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not spray on an open flame or other ignition source.

If in eyes: Rinse cautiously with water for several minutes and

remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists.

If on skin: Wash with plenty of soap and water.

If inhaled: Remove person to fresh air and keep comfortable for breathing

**If swallowed: Rinse mouth and get medical attention if you feel unwell.**

**Color:** Grey

**Gloss Level (60°):** 90° Min

**PH:** NA

**Viscosity :** 51 ± 1 KU

**Density:** 0.918 ± 0.05

**Odor:** Strong

**Flash point:** 4 °C

**Weight per Gallon:**

7.65 ± 0.25% lb/gal.

**Solids by weight:** 43 ± 1%

**Solids by volume:** 34 ± 1%

**Film Thickness:**

**Wet (WFT) :** 3-5 mils

**Dry (DFT):** 1.0-1.5 mils, 25.0-37.5 microns,

**Theoretical coverage:**

364-546sq ft/gal, 9-13 m<sup>2</sup>/L, @ 1-1.5 mils DFT

**Practical coverage:**

(At an efficiency of 85%)

The coverage is 309-464 sq ft / gal, 8-11 m<sup>2</sup> / L @ 1-1.5 mils DFT dry film thickness)

**Dry to touch:** 15 to 20 minutes

**Time to recoat:** 1 to 2 hours

**Application**

**Temperature (°C):** 10 to 30 °C (50° to 86 °F)

**Humidity:** Ideal: 50%. Maximum: 65%.

**Equipment**

**Recommendations:**

(Comparable Equipment Also Suitable).

**AIRLESS SPRAY :**

(filter through cheesecloth when the Airless paint sprayer is used)

**Do not induce vomiting.**

Consult the form of safety data (SDS) and an other information on label before using this product.

**WASTE DISPOSAL:**

Reach your municipality about proper disposal procedure or give leftover paint to someone who could use it, a neighbor or friend, a recreational service or a non-profit organization. For more information, visit [www.eco-peinture.ca](http://www.eco-peinture.ca) if you reside in Quebec. Do not leftover paint down the drain.

**PHYSICAL PROPERTIES:**

The values shown are theoretical and may vary slightly from the finished product.

**WARRANTY:**

In lieu of all other warranties or guarantees, express or implied, by contract or law, manufacturer's liability hereby limited to replacement of the merchandise herein if found to be defective upon inspection by it. Manufacturer shall no be liable for any representations, warranties (express or implied) made by any of its agents, representatives or employees regarding the merchandise or product contained herein.

Issue Date: 09/06/2016.

Pressure 2200-2400 psi

Tip 0.013□ – 0.015□

Reduction About 10- 15 %.with.  
M0061-00



**Packaging:** Available sizes:

946 ml, 3,79 L, 18,9 L, et 200 L.

