

DESCRIPTION

A high gloss, fast dry alkyd based paint with very good corrosion resistance and durable finish.

RELATED PRODUCTS:

M2090-00 WHITE- M2090-20 MEDIUM- M2030-00 BLACK-M2011-00 SECURITY YELLOW-M2090-21 MEDIUM BASE COLOUR-M2090-60 ACCENT-M2090-61 ACCENT BASE COLOUR-M2130-00 BLACK-M2090-90 HAMMER TONE- M2090-91 GREY WITH COLOUR- M2025-00 RED.

USAGE:

Recommended for maintenance of steel structures and equipment. For galvanized steel and aluminum a tie coat of M0271-00 should be used first before applying primer.

For best results, apply (2) two coats of finish.

SURFACE PREPARATION:

New steel : Remove all foreign matter such as oil, grease, soil drawing and cutting compounds and other surface contaminants by the use of appropriate solvent. If present, remove loose mill scale and loose rust by hand brushing, sanding or other hand impact or power tools. Apply primer as recommended.

Old steel : (painted and unpainted surface)

Remove all loose mill scale, loose rust and loose paint with power brushes, power grinders or power sanders. Check compatibility of primer on old painted surface by making a small test patch before priming the whole surface

DIRECTIONS FOR USE:

Stir well before using. Apply at a temperature between 10-30 °C using a brush, roller or spray equipment. Clean tools with diluents or xylol.

STORAGE: Keep the product in a dry and cool area. Keep away from open flames and sparks. The storage temperature is : (5- 30) °C.

SAFETY INFORMATION: Lead: None

DANGER.Flammable liquid and vapour. Causes mild skin irritation. May be fatal if swallowed and enter airways. Harmful if inhaled..

Wear protective eyewear, waterproof gloves, and protective clothing.

Store locked up. Keep cool. Protect from sunlight.Keep away from heat,hot surfaces,sparks,open flames and other ignition sources .No smoking .Do not spray on an open flame or other ignition source.

If in eyes: Rinse cautiously with water for several minutes and

remove contacts if present and easy todo.Continue rinsing and get medical attention if eye irritation persists.

If on skin: Wash with plenty of soap and water.

If Inhaled: Remove person to fresh air and keep comfortable for breathing

If swallowed: Rinse mouth and get medical attention if you feel unwell.

Do not induce vomiting.

Consult the form of safety data (SDS) and an other information on label before using this product.

Color: White.

Gloss Level (60°): 90° ± 5

PH: NA

Viscosity:73 ± 3 KU

Density: 1.18 ± 0.05

Odor: Strong

Flash point: 28 °C

V.O.C: 570 g/l.

Weight per Gallon:

9.75 ± 0.25% lb/gal.

Solids by weight: 50 ± 1%

Solids by volume: 32 ± 1%

Film Thickness:

Wet (WFT) : 3.1-4.6 mils

Dry (DFT): 1.0-1.5 mils,25.0-37.5 microns,

Theoretical coverage:

300-500 sq ft/gal,8-12m2/L,@

1-1.5 mils DFT.

Practical coverage:

(At an efficiency of 85%)

The coverage is 291-436 sq ft / gal, 7-10 m2 / L @ 1-1.5 mils DFT dry film thickness)

Dry to touch: 15 to 20 minutes

Time to recoat: 1 to 2 hours

Application

Temperature (°C): 10 to 30 °C (50° to 86 °F)

Humidity: Ideal: 50%. Maximum: 65%.

Equipment recommendations

(Comparable Equipment Also Suitable).

BRUSH: Use a nylon / polyester brush.

ROLLER: Use a 3/8 a -3/4" nap synthetic roller cover.

WASTE DISPOSAL:

Reach your municipality about proper disposal procedure or give leftover paint to someone who could use it, a neighbor or friend, a recreational service or a non-profit organization. For more information, visit www.eco-peinture.ca if you reside in Quebec. Do not leftover paint down the drain.

PHYSICAL PROPERTIES:

The values shown are theoretical and may vary slightly from the finished product.

WARRANTY:

In lieu of all other warranties or guarantees, express or implied, by contract or law, manufacturer's liability hereby limited to replacement of the merchandise herein if found to be defective upon inspection by it. Manufacturer shall no be liable for any representations, warranties (express or implied) made by any of its agents, representatives or employees regarding the merchandise or product contained herein.

Issue Date: 07/06/2016.

AIRLESS SPRAY :

(filter through cheesecloth when the Airless paint sprayer is used)

Pressure: 2200-2400 psi

Tip size: 0.013□ – 0.015□

Reduction About 10 % with.
M0061-00.



Packaging: Available sizes:

946 ml, 3,79 L, 18,9 L, et 200 L.

